

Messrs.

Date:

APPROVAL SHEET

Product Name : Medium Voltage Multilayer Ceramic Chip Capacitors

Part No. : FM Series

Description : Size 0402~2225, C0G(NPO)/X7R/Y5V, 100Vdc to 630Vdc

PREPARED BY	APPROVED BY

信昌電子陶瓷股份有限公司

PROSPERITY DIELECTRICS CO., LTD.

桃園縣蘆竹鄉南山路二段 220-1 號 <http://www.pdc.com.tw>

Tel: 03-322-4471 ext: Fax: 03-322-5231 / 03-321-2215

Contact: _____ Mobile: _____

SPECIFICATION FOR

MEDIUM VOLTAGE MULTILAYER CERAMIC CHIP CAPACITORS

Part No. : FM Series

Description : Size 0402~2225, C0G(NPO)/X7R/Y5V, 100Vdc to 630Vdc

<u>DRAWN BY</u>	<u>CHECKED BY</u>	<u>APPROVED BY</u>
蕭敏珍	蔡永承	巫宏俊

1. INTRODUCTION

FM Series green type capacitors are manufactured by using green materials without lead and cadmium. These capacitors feature series connection of multi-layer capacitor units in a MLCC to realize high voltage performance. Reliable performances are built-in through exact formulation of dielectric powders, preparation of conductive paste, advanced automatic manufacturing, and strict quality control to assure excellent control in dielectric thickness, electrode integrity, and electrode-to-termination continuity.

2. FEATURES

- a. High Voltage in a given case size.
- b. High reliability and stability.
- c. RoHS & HALOGEN Compliant

3. APPLICATIONS

- a. DC to DC converter.
- b. High voltage coupling/DC blocking.
- c. Back-lighting inverters.
- d. Sunbbers in high frequency power convertors.


4.HOW TO ORDER

<u>FM</u>	<u>31</u>	<u>X</u>	<u>104</u>	<u>K</u>	<u>251</u>	<u>E</u>	<u>E</u>	<u>G</u>
PDC Family	Size	Dielectric	Capacitance	Tolerance	Rated voltage	Packaging	Thickness	Control Code
Table1.	Table2	Table3	Table4	Table5	Table6	Table7	Table8	Table9

Reference document with No.11 reference table detail.

5. EXTERNAL DIMENSIONS

Size Inch (mm)	L (mm)	W (mm)	Thickness Spec T(mm) code	M _B min (mm)
0402 (1005)	1.00±0.15/-1.0	0.50±0.15/-1.0	See No.11 Reference Table	0.25 +0.05/-0.10
0603 (1608)	1.60±0.20	0.80±0.15		0.40±0.15
0805 (2012)	2.10±0.20	1.25±0.20		0.50±0.20
1206 (3216)	3.30±0.30	1.60±0.30/-0.10		0.60±0.20
1210 (3225)	3.30±0.40	2.50±0.30		0.75±0.35
1808 (4520)	4.60±0.50	2.00±0.20		0.75±0.35
1812 (4532)	4.60±0.50	3.20±0.30		0.75±0.35
1825 (4563)	4.60±0.50	6.30±0.40		0.75±0.35
2220 (5750)	5.70±0.50	5.00±0.40		0.85±0.35
2225 (5763)	5.70±0.50	6.30±0.40		0.85±0.35



6. GENERAL ELECTRICAL DATA

Dielectric	C0G(NPO)		X7R	Y5V
Size	0402, 0603, 0805, 1206, 1210, 1808 ,1812, 1825, 2220, 2225		0603, 0805, 1206, 1210,1808, 1812, 1825, 2220, 2225	0805, 1206, 1210, 1812
Rated voltage (WVDC)	100V, 200V, 250V, 500V, 630V		100V, 200V,250V,500V, 630V	100V, 200V, 250V
Capacitance range*	0.5pF ~ 180nF		100pF ~ 820nF	10nF to 820nF
Capacitance tolerance	Reference to Table5		Reference to Table5	Reference to Table5
Tan δ			≤ 2.5%	≤5%
	Cap. Rang	Q Spec.		
	Cap<30pF:	Q≥400+20C		
	Cap≥30pF:	Q≥1000		
Capacitance & Tan δ Test Condition	Measured at the condition of 30~70% related humidity.			
	For 25℃ at ambient temperature		Preconditioning for Class II MLCC: Perform a heat treatment at 150±10℃ for 1 hour, then leave in ambient condition for 24±2 hours before measurement.	
	Cap. Rang	Test Condition	1.0±0.2Vrms, 1.0kHz±10%, at 25℃ ambient temperature.	1.0±0.2Vrms,1.0kHz±10%, at 20℃ ambient temperature.
	Cap≤1000pF	1.0±0.2Vrms, 1.0MHz±10%		
	Cap>1000pF,	1.0±0.2Vrms, 1.0kHz±10%		
	Insulation resistance at Ur	≥100GΩ or R•C≥ 500Ω•F whichever is smaller		≥10GΩ or R•C≥100Ω•F whichever is smaller
Operating temperature	-55 to +125℃			-25 to +85℃
Capacitance characteristic	±30ppm / ℃		±15%	+30/-80%
Termination	Cu (or Ag)/Ni/Sn (lead-free termination)			

7.CAPACITANCE RANGE

7-1. C0G(NPO) Dielectric

Dimension		0402	0603				0805					1206				
Cap(pF)	code	100V	100V	200V	250V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V	
0.5	0R5	N	S	S	S	A	A	A	A	A						
1.0	1R0	N	S	S	S	A	A	A	A	A						
1.2	1R2	N	S	S	S	A	A	A	A	A	X			X		
1.5	1R5	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
1.8	1R8	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
2.2	2R2	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
2.7	2R7	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
3.3	3R3	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
3.9	3R9	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
4.7	4R7	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
5.6	5R6	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
6.8	6R8	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
8.2	8R2	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
10	100	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
12	120	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
15	150	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
18	180	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
22	220	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
27	270	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
33	330	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
39	390	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
47	470	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
56	560	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
68	680	N	S	S	S	A	A	A	A	A	X	X	X	X	X	
82	820	N	S	S	S	A	A	A	X	X	X	X	X	X	X	
100	101	N	S	S	S	A	A	X	X	X	X	X	X	X	X	
120	121	N	S	S	S	A	A	X	C	C	X	X	X	X	X	
150	151	N	S	S	S	A	X	X	C	C	X	X	X	X	X	
180	181	N	S	S	S	A	X	C	C	C	X	X	X	X	X	
220	221	N	S	S	S	A	C	C	C	C	X	X	X	X	X	
270	271		S	B	B	A	C	C	C	C	X	X	M	M	M	
330	331		S	B	B	A	C	C	C	C	X	X	M	M	M	
390	391		S	B	B	X	C	C	C	C	X	X	M	M	M	
470	471		S	B	B	X	C	C	C	C	X	M	M	M	M	
560	561		S	B	B	X	C	C	C	C	X	M	C	C	C	
680	681		S	B	B	X	C	C	C	C	X	M	C	C	C	
820	821		S	B	B	X	C	C	C	C	X	M	E	E	E	
1000	102		S			X	C	C	C	C	X	M	E	E	E	
1200	122		B			X	C	C	C	C	X	M	E	E	E	
1500	152		B			X	C	C	C	C	X	C	E	E	E	
1800	182					X	C	C	C	C	X	C	E	E	E	
2200	222					X	C	C	C	C	X	C	E	E	E	
2700	272					C					X	C	E	E	E	
3300	332					C					X	C	E	E	E	
3900	392					C					X	E	E	E	E	
4700	472					C					X	E	E	E	E	
5600	562					C					X	E	E	E	E	
6800	682					C					M	E	E			
8200	822										C	E	E			
10000	103										C					
12000	123										T					
15000	153										T					
18000	183										T					
22000	223										T					

7-1. C0G(NPO) Dielectric

Dimension		1210					1808					1812				
Cap(pF)	code	100V	200V	250V	500V	630V	100	200	250	500V	630V	100V	200V	250V	500V	630V
2.2	2R2						C	C	C	C	C					
2.7	2R7						C	C	C	C	C					
3.3	3R3						C	C	C	C	C					
3.9	3R9						C	C	C	C	C					
4.7	4R7						C	C	C	C	C					
5.6	5R6						C	C	C	C	C					
6.8	6R8						C	C	C	C	C					
8.2	8R2						C	C	C	C	C					
10	100	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
12	120	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
15	150	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
18	180	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
22	220	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
27	270	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
33	330	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
39	390	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
47	470	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
56	560	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
68	680	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
82	820	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
100	101	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
120	121	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
150	151	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
180	181	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
220	221	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
270	271	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
330	331	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
390	391	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
470	471	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
560	561	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
680	681	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
820	821	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
1000	102	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
1200	122	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
1500	152	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
1800	182	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
2200	222	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
2700	272	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
3300	332	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
3900	392	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
4700	472	C	C	C	C	C	C	C	C	F	F	C	C	C	C	C
5600	562	C	C	C	C	C	C	E	E	F	F	C	C	C	C	C
6800	682	E	E	E	E	E	C	E	E	F	F	C	C	C	C	C
8200	822	E	E	E	E	E	E	F	F	F	F	C	C	C	C	C
10000	103	E	F	F	F	F	E	F	F	F	F	C	C	C	C	C
12000	123	E	F	F	F	F	F	F	F			C	E	E	E	E
15000	153	F	G	G	G	G	F	F	F			C	E	E	E	E
18000	183	G	G	G			F					E	F	F	F	F
22000	223	G	G	G			F					E	F	F	F	F
27000	273	G										F	G	G	G	G
33000	333	G										F	G	G	G	G
39000	393											G	G	G		
47000	473											G	G	G		
56000	563											G				
68000	683											G				

7-1. C0G(NPO) Dielectric

Dimension		1825					2220					2225				
Cap(pF)	code	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
10	100	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
12	120	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
15	150	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
18	180	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
22	220	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
27	270	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
33	330	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
39	390	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
47	470	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
56	560	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
68	680	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
82	820	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
100	101	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
120	121	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
150	151	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
180	181	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
220	221	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
270	271	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
330	331	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
390	391	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
470	471	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
560	561	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
680	681	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
820	821	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
1000	102	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
1200	122	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
1500	152	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
1800	182	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
2200	222	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
2700	272	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
3300	332	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
3900	392	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
4700	472	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
5600	562	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
6800	682	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
8200	822	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
10000	103	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
12000	123	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
15000	153	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
18000	183	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
22000	223	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
27000	273	E	E	E	F	F	E	E	E	F	F	E	E	E	E	E
33000	333	E	E	E	F	F	E	F	F	F	F	E	E	E	E	E
39000	393	E	F	F	G	G	E	F	F	G	G	E	F	F	F	F
47000	473	E	F	F	G	G	E	G	G	G	G	E	F	F	F	F
56000	563	F	G	G	G	G	F	G	G	G	G	E	G	G	G	G
68000	683	F	G	G	G	G	F	G	G			F	G	G	G	G
82000	823	G	G	G			G	G	G			F	G	G	G	G
100000	104	G					G					G	G	G		
120000	124						G					G	G	G		
150000	154											G				
180000	184											G				

7.2 X7R Dielectric

Dimension		0603			0805					1206				
Cap(pF)	code	100V	200V	250V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
100	101	S	B	B	X	X	X	X	X	X	C	C	C	C
120	121	S	B	B	X	X	X	X	X	X	C	C	C	C
150	151	S	B	B	X	X	X	X	X	X	C	C	C	C
180	181	S	B	B	X	X	X	X	X	X	C	C	C	C
220	221	S	B	B	X	X	X	X	X	X	C	C	C	C
270	271	S	B	B	X	X	X	X	X	X	C	C	C	C
330	331	S	B	B	X	X	X	X	X	X	C	C	C	C
390	391	S	B	B	X	X	X	X	X	X	C	C	C	C
470	471	S	B	B	X	X	X	X	X	X	C	C	C	C
560	561	S	B	B	X	X	X	X	X	X	C	C	C	C
680	681	S	B	B	X	X	X	X	X	X	C	C	C	C
820	821	S	B	B	X	X	X	X	X	X	C	C	C	C
1000	102	S	B	B	X	X	X	X	X	X	C	C	C	C
1200	122	S	B	B	X	X	X	X	X	X	C	C	C	C
1500	152	S	B	B	X	X	X	X	X	X	C	C	C	C
1800	182	S	B	B	X	X	X	X	X	X	C	C	C	C
2200	222	S	B	B	X	X	X	X	X	X	C	C	C	C
2700	272	S	B	B	X	X	X	X	X	X	C	C	C	C
3300	332	S	B	B	X	X	X	X	X	X	C	C	C	C
3900	392	S	B	B	X	X	X	X	X	X	C	C	C	C
4700	472	S	B	B	X	X	X	C	C	X	C	C	C	C
5600	562	S	B	B	X	X	X	C	C	X	C	C	C	C
6800	682	S	B	B	X	X	X	C	C	X	C	C	C	C
8200	822	S	B	B	X	C	C	C	C	X	C	C	C	C
10000	103	S	B	B	X	C	C	C	C	X	C	C	C	C
12000	123	B	B	B	X	C	C	C	C	X	C	C	C	C
15000	153	B	B	B	X	C	C	C	C	X	C	C	C	C
18000	183	B			X	C	C	C	C	X	C	C	C	C
22000	223	B			X	C	C	C	C	X	C	C	E	E
27000	273	B			C	C	C			X	C	C	E	E
33000	333	B			C	C	C			X	E	E	E	E
39000	393	B			C	C	C			X	E	E	E	E
47000	473	B			C	C	C			X	E	E	E	E
56000	563	B			C	C	C			X	E	E	E	E
68000	683	B			C	C	C			X	E	E		
82000	823	B			C	C				C	E	E		
100000	104	B			C	C				C	E	E		
120000	124				C					C				
150000	154				C					E				
180000	184				C					E				
220000	224				C					E				
270000	274									E				
330000	334									E				
390000	394									E				
470000	474				I					E				
560000	564									P				
680000	684									P				
820000	824									P				

7.2 X7R Dielectric

Dimension		1210					1808					1812				
Cap(pF)	code	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
150	151						C	C	C	C	C					
180	181						C	C	C	C	C					
220	221	M	M	M	C	C	C	C	C	C	C					
270	271	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
330	331	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
390	391	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
470	471	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
560	561	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
680	681	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
820	821	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
1000	102	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
1200	122	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
1500	152	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
1800	182	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
2200	222	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
2700	272	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
3300	332	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
3900	392	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
4700	472	M	M	M	C	C	C	C	C	C	C	C	C	C	C	C
5600	562	M	M	M	C	C	E	E	E	F	F	C	C	C	C	C
6800	682	M	M	M	C	C	E	E	E	F	F	C	C	C	C	C
8200	822	M	M	M	C	C	E	E	E	F	F	C	C	C	C	C
10000	103	M	M	M	C	C	E	E	E	F	F	C	C	C	C	C
12000	123	M	M	M	C	C	E	E	E	F	F	C	C	C	C	C
15000	153	M	M	M	C	C	E	E	E	F	F	C	C	C	C	C
18000	183	M	M	M	C	C	E	E	E	F	F	C	C	C	C	C
22000	223	M	M	M	C	C	E	E	E	F	F	C	C	C	C	C
27000	273	M	M	M	E	E	E	E	E	F	F	C	C	C	C	C
33000	333	M	M	M	E	E	E	E	E	F	F	C	C	C	C	C
39000	393	M	M	M	E	E	E	E	E	F	F	C	C	C	C	C
47000	473	M	C	C	E	E	E	E	E	F	F	C	C	C	C	C
56000	563	M	C	C	E	E	E	E	E	F	F	C	C	C	F	F
68000	683	M	E	E	F	F	E	E	E	F	F	C	C	C	F	F
82000	823	M	E	E	G	G	E	E	E	F	F	C	C	C	F	F
100000	104	M	E	E	G	G	E	E	E	F	F	E	C	C	F	F
120000	124	M	E	E	G	G	E	E	E			E	C	C	G	G
150000	154	C	G	G	G	G	E	E	E			E	F	F	G	G
180000	184	C	G	G			E	F	F			E	F	F	G	G
220000	224	C	G	G			E	F	F			E	F	F	G	G
270000	274	E	G	G			F	F	F			E	F	F	G	
330000	334	E	G	G			F	F	F			E	F	F	G	
390000	394	G	G	G			F	F	F			E	F	F	G	
470000	474	G	G	G			F	F	F			E	F	F	G	
560000	564	G	G	G			F	F	F			F	G	G		
680000	684	F	G	G			F					F	G	G		
820000	824	F					F					F	G	G		

7.2 X7R Dielectric

Dimension		1825					2220					2225				
Cap(pF)	code	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
1000	102	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1200	122	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1500	152	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1800	182	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
2200	222	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
2700	272	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
3300	332	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
3900	392	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
4700	472	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
5600	562	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
6800	682	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
8200	822	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
10000	103	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
12000	123	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
15000	153	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
18000	183	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
22000	223	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
27000	273	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
33000	333	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
39000	393	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
47000	473	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
56000	563	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
68000	683	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
82000	823	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
100000	104	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
120000	124	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
150000	154	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
180000	184	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
220000	224	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
270000	274	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
330000	334	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
390000	394	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
470000	474	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
560000	564	F	F	F	G	G	F	F	F	G	G	F	F	F	F	F
680000	684	F	F	F	G	G	F	F	F	G	G	F	F	F	F	F
820000	824	F	F	F	H	H	F	F	F	H	H	F	F	F	G	G

7-3. Y5V Dielectric

Dimension		0805			1206			1210			1812		
Cap(pF)	code	100V	200V	250V	100V	200V	250V	100V	200V	250V	100V	200V	250V
10	103	X	X	X	X	X	X	M	M	M	C	C	C
15	153	X	X	X	X	X	X	M	M	M	C	C	C
22	223	X	X	X	X	X	X	M	M	M	C	C	C
33	333	X	X	X	X	X	X	M	M	M	C	C	C
47	473	X	X	X	X	X	X	M	M	M	C	C	C
68	683	X	X	X	X	X	X	M	M	M	C	C	C
100	104	X			X	X	X	M	M	M	C	C	C
150	154				M	M	M	M	M	M	C	C	C
220	224				M			M			C	C	C
330	334							M			C	C	C
470	474										C	C	C
680	684										C	C	C



8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																												
1.	Visual and Dimensions	---	* No remarkable defect. * Dimensions to confirm to individual specification sheet.																												
2.	Capacitance	Class I: C0G(NP0)	* Shall not exceed the limits given in the detailed spec.																												
3.	Q/ D.F. (Dissipation Factor)	Cap≤1000pF, 1.0±0.2Vrms, 1MHz±10% Cap>1000pF, 1.0±0.2Vrms, 1KHz±10% Class II: (X7R, Y5V) 1.0±0.2Vrms, 1kHz±10%	<table><tr><th>Dielectric</th><th>Rated vol.(V)</th><th>Q/D.F.</th><th>Remark</th></tr><tr><td>Class I(NPO)</td><td>All</td><td>Q≥1000 Q≥400+20C</td><td>Cap≥30pF Cap<30pF</td></tr><tr><td>Class II(X7R)</td><td>≥ 100</td><td>D.F. < 2.5% D.F. < 3.0%</td><td>0603≥0.047μF; 0805≥0.18μF, 1206≥0.47μ F</td></tr><tr><td>Class II(Y5V)</td><td>≥ 100</td><td>D.F. < 5.0%</td><td></td></tr></table>	Dielectric	Rated vol.(V)	Q/D.F.	Remark	Class I(NPO)	All	Q≥1000 Q≥400+20C	Cap≥30pF Cap<30pF	Class II(X7R)	≥ 100	D.F. < 2.5% D.F. < 3.0%	0603≥0.047μF; 0805≥0.18μF, 1206≥0.47μ F	Class II(Y5V)	≥ 100	D.F. < 5.0%													
Dielectric	Rated vol.(V)	Q/D.F.	Remark																												
Class I(NPO)	All	Q≥1000 Q≥400+20C	Cap≥30pF Cap<30pF																												
Class II(X7R)	≥ 100	D.F. < 2.5% D.F. < 3.0%	0603≥0.047μF; 0805≥0.18μF, 1206≥0.47μ F																												
Class II(Y5V)	≥ 100	D.F. < 5.0%																													
4.	Temperature Coefficient	With no electrical load. <table><tr><th>T.C.</th><th>Operating Temp</th></tr><tr><td>C0G(NPO)</td><td>-55~125°C at 25°C</td></tr><tr><td>X7R</td><td>-55~125°C at 25°C</td></tr><tr><td>Y5V</td><td>-25~85°C at 20°C</td></tr></table>	T.C.	Operating Temp	C0G(NPO)	-55~125°C at 25°C	X7R	-55~125°C at 25°C	Y5V	-25~85°C at 20°C	<table><tr><th>T.C.</th><th>Capacitance Change</th></tr><tr><td>C0G(NPO)</td><td>Within ±30ppm/°C</td></tr><tr><td>X7R</td><td>Within ±15%</td></tr><tr><td>Y5V</td><td>Within +30%/-80%</td></tr></table>	T.C.	Capacitance Change	C0G(NPO)	Within ±30ppm/°C	X7R	Within ±15%	Y5V	Within +30%/-80%												
T.C.	Operating Temp																														
C0G(NPO)	-55~125°C at 25°C																														
X7R	-55~125°C at 25°C																														
Y5V	-25~85°C at 20°C																														
T.C.	Capacitance Change																														
C0G(NPO)	Within ±30ppm/°C																														
X7R	Within ±15%																														
Y5V	Within +30%/-80%																														
5.	Insulation Resistance	<table><tr><th>Rated vol.(V)</th><th>Apply Voltage</th><th>Test Condition</th></tr><tr><td>= 100</td><td>1 times of UR</td><td>Max. 120 sec</td></tr><tr><td>>100</td><td>1 times of UR</td><td>60 sec</td></tr><tr><td>> 500</td><td>500VDC</td><td>60 sec</td></tr></table>	Rated vol.(V)	Apply Voltage	Test Condition	= 100	1 times of UR	Max. 120 sec	>100	1 times of UR	60 sec	> 500	500VDC	60 sec	<table><tr><th>Dielectric</th><th>Requirements</th></tr><tr><td>Class I</td><td>≥100GΩ or RxC≥ 500Ω-F whichever is smaller</td></tr><tr><td>Class II</td><td>≥10GΩ or RxC≥ 100Ω-F whichever is smaller.</td></tr></table>	Dielectric	Requirements	Class I	≥100GΩ or RxC≥ 500Ω-F whichever is smaller	Class II	≥10GΩ or RxC≥ 100Ω-F whichever is smaller.										
Rated vol.(V)	Apply Voltage	Test Condition																													
= 100	1 times of UR	Max. 120 sec																													
>100	1 times of UR	60 sec																													
> 500	500VDC	60 sec																													
Dielectric	Requirements																														
Class I	≥100GΩ or RxC≥ 500Ω-F whichever is smaller																														
Class II	≥10GΩ or RxC≥ 100Ω-F whichever is smaller.																														
6.	Solderability	* Solder temperature: 235±5°C for (0603~1210) * Solder temperature: 245±5°C for (1808~2225) * Dipping time: 2±0.5 sec.	75% min. coverage of all metalized area.																												
7.	Dielectric Strength	<table><tr><th>Rated vol.(V)</th><th>Condition</th></tr><tr><td>≤ 250</td><td>2 times of UR</td></tr><tr><td>250<V≤500</td><td>1.5 times of UR</td></tr><tr><td>630≤V≤3000V</td><td>1.2 times of UR</td></tr><tr><td>3000<V≤5000V</td><td>1.1 times of UR</td></tr><tr><td>>5000V</td><td>1.0 times of UR</td></tr></table> * Duration: 1 to 5 sec. * Charge and discharge current less than 50mA.	Rated vol.(V)	Condition	≤ 250	2 times of UR	250<V≤500	1.5 times of UR	630≤V≤3000V	1.2 times of UR	3000<V≤5000V	1.1 times of UR	>5000V	1.0 times of UR	* No evidence of damage or flashover during test.																
Rated vol.(V)	Condition																														
≤ 250	2 times of UR																														
250<V≤500	1.5 times of UR																														
630≤V≤3000V	1.2 times of UR																														
3000<V≤5000V	1.1 times of UR																														
>5000V	1.0 times of UR																														
8.	Resistance to Soldering Heat	* Solder temperature: 260±5°C * Dipping time: 10±1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 48±4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	* No remarkable damage. <table><tr><th>Dielectric</th><th>Cap Change</th><th>Q/D.F. & IR</th></tr><tr><td>Class I(NPO)</td><td>Within ±2.5% or ±0.25pF whichever is larger.</td><td rowspan="3">To meet Initial requirement</td></tr><tr><td>Class II(X7R)</td><td>within ±7.5%</td></tr><tr><td>Class II(Y5V)</td><td>within ±20%</td></tr></table> * 25% max. leaching on each edge.	Dielectric	Cap Change	Q/D.F. & IR	Class I(NPO)	Within ±2.5% or ±0.25pF whichever is larger.	To meet Initial requirement	Class II(X7R)	within ±7.5%	Class II(Y5V)	within ±20%																		
Dielectric	Cap Change	Q/D.F. & IR																													
Class I(NPO)	Within ±2.5% or ±0.25pF whichever is larger.	To meet Initial requirement																													
Class II(X7R)	within ±7.5%																														
Class II(Y5V)	within ±20%																														
9.	Temperature Cycle	* Conduct the five cycles according to the temperatures and time. <table><tr><th>Step</th><th>Temp. (°C)</th><th>Time (min.)</th></tr><tr><td>1</td><td>Min. operating emp. +0/-3</td><td>30±3</td></tr><tr><td>2</td><td>Room temp.</td><td>2~3</td></tr><tr><td>3</td><td>Max. operating temp. +3/-0</td><td>30±3</td></tr><tr><td>4</td><td>Room temp.</td><td>2~3</td></tr></table> * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 48±4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	Step	Temp. (°C)	Time (min.)	1	Min. operating emp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	* No remarkable damage. <table><tr><th>Dielectric</th><th>I.R</th><th>Cap Change</th><th>Q/D.F</th></tr><tr><td>Class I(NPO)</td><td rowspan="3">To meet Initial requirement</td><td>Within ±2.5% or ±0.25pF whichever is larger.</td><td>≤ 1.0(Q) × Initial requirement</td></tr><tr><td>Class II(X7R)</td><td>within ±7.5%</td><td rowspan="2">≤ 1.5(D.F.) × Initial requirement</td></tr><tr><td>Class II(Y5V)</td><td>within ±20%</td></tr></table>	Dielectric	I.R	Cap Change	Q/D.F	Class I(NPO)	To meet Initial requirement	Within ±2.5% or ±0.25pF whichever is larger.	≤ 1.0(Q) × Initial requirement	Class II(X7R)	within ±7.5%	≤ 1.5(D.F.) × Initial requirement	Class II(Y5V)	within ±20%
Step	Temp. (°C)	Time (min.)																													
1	Min. operating emp. +0/-3	30±3																													
2	Room temp.	2~3																													
3	Max. operating temp. +3/-0	30±3																													
4	Room temp.	2~3																													
Dielectric	I.R	Cap Change	Q/D.F																												
Class I(NPO)	To meet Initial requirement	Within ±2.5% or ±0.25pF whichever is larger.	≤ 1.0(Q) × Initial requirement																												
Class II(X7R)		within ±7.5%	≤ 1.5(D.F.) × Initial requirement																												
Class II(Y5V)		within ±20%																													

8.RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements				
10.	Humidity (Damp Heat) Steady State	* Test temp.: 40±2℃ * Humidity: 90~95%RH * Test time: 500+24/-0 hrs. * Measurement to be made after keeping at room temp. for 24±2 hrs. (Class I) or 48±4 hrs. (Class II).	* No remarkable damage.				
			Dielectric	I.R	Cap Change	Q/D.F	
			Class I(NPO)	≥1G_ or RxC≥ 50Ω-F whichever is smaller.	within ±5.0% or ± 0.5pF whichever is larger	Cap ≥30pF 10pF ≤ Cap < 30pF Cap < 10pF	Q≥350; Q≥275+2.5C Q≥200+10C
			Class II(X7R)		within ±12.5%	D.F. ≤ 200% × Initial requirement	
Class	within ±30%	D.F. ≤ 200% × Initial requirement					
11.	Humidity (Damp Heat) Load	* Test temp.: 40±2℃ * Humidity: 90~95% RH * Test time: 500+24/-0hrs. *To apply voltage :rated voltage * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	* No remarkable damage.				
			* No remarkable damage.				
			Dielectric	I.R	Cap Change	Q/D.F	
			Class I(NPO)	≥1GΩ or RxC≥ 50Ω-F whichever is smaller.	within ±7.5% or ±0.75pF whichever is larger	Cap ≥30pF 10pF ≤ Cap < 30pF Cap <10pF	Q≥350; Q≥275+2.5C Q≥200+10C
Class II(X7R)	within ±12.5%	D.F. ≤ 200% × Initial requirement					
Class II(Y5V)	within ±30%	D.F. ≤ 200% × Initial requirement					
12.	High Temperature Load (Endurance)	* Test temp.: NP0, X7R : 125±3℃ Y5V: 85±3℃					
		Dielectric	Rated vol.(V)	Apply Voltage			
		NP0, X7R ,Y5V	≤ 250	2.0 times of U _R			
			250 <V ≤ 500	1.5 times of U _R			
			= 630	1.2 times of U _R			
		Exception item(X7R only):					
		Rated vol.(V)	Size	Cap. Range	Apply Voltage		
		100	0805	≥ 124	1.5 times of U _R		
			1206	≥ 105			
			1210				
1825							
2220							
2225							
200 & 250	1210	> 224					
	1812	> 474					
	1825	≥ 105					
	2220						
	2225						
</							


8.RELIABILITY TEST CONDITIONS AND REQUIREMENTS (Cont.)

No.	Item	Test Condition	Requirements								
13	Resistance to Flexure of Substrate	* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1mm per second until the deflection becomes 1mm. 	* No remarkable damage. <table border="1"><thead><tr><th>Dielectric</th><th>Cap Change</th></tr></thead><tbody><tr><td>Class I(NPO)</td><td>within ±3.0% or ±0.3pF whichever is larger</td></tr><tr><td>Class II(X7R)</td><td>within ±12.5%</td></tr><tr><td>Class II(Y5V)</td><td>within ±30%</td></tr></tbody></table> (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.)	Dielectric	Cap Change	Class I(NPO)	within ±3.0% or ±0.3pF whichever is larger	Class II(X7R)	within ±12.5%	Class II(Y5V)	within ±30%
Dielectric	Cap Change										
Class I(NPO)	within ±3.0% or ±0.3pF whichever is larger										
Class II(X7R)	within ±12.5%										
Class II(Y5V)	within ±30%										
14.	Adhesive Strength of Termination	* Capacitors mounted on a substrate. A force of 5N(≤0603) or 10N(> 0603) applied perpendicular to the place of substrate and parallel the line joining the center of terminations for 10±1 second. 	* No remarkable damage or removal of the terminations.								
15.	Vibration Resistance	* Vibration frequency: 10~55 Hz/min. * Total amplitude: 1.5mm * Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.)	* No remarkable damage. * Cap change and Q/D.F.: To meet initial spec.								

9. PACKAGE DIMENSION AND QUANTITY


Size	Thickness (mm)	Paper tape		Plastic tape	
		7" reel	13" reel	7" reel	13" reel
0402 (1005)	0.50±0.05	10k	50K	-	-
0603 (1608)	0.80±0.07	4k	15k	-	-
	0.80+0.15/-0.10	4k	15k	-	-
0805 (2012)	0.60±0.10	4k	15k	-	-
	0.80±0.10	4k	15k	-	-
	1.25±0.10	-	-	3k	10k
	1.25±0.20	-	-	3k	-
1206 (3216)	0.80±0.10	4k	15k	-	-
	0.95±0.10	-	-	3k	10k
	1.25±0.10	-	-	3k	10k
	1.60±0.20	-	-	2k	-
	1.60 +0.30/-0.10	-	-	2k	-
1210 (3225)	0.95±0.10	-	-	3k	10k
	1.25±0.10	-	-	3k	10k
	1.60±0.20	-	-	2k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	1k	-
1808 (4520)	1.25±0.10	-	-	2k	-
	1.60±0.20	-	-	2k	-
	2.00±0.20	-	-	1k	-
1812 (4532)	1.25±0.10	-	-	1k	-
	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	3k
1825 (4563)	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
2220 (5750)	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
2225 (5763)	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-

Unit: pieces




Size	0402, 0603, 0805, 1206, 1210			1808, 1812, 1825, 2220, 2225
Reel size	7"	10"	13"	7"
C	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2
W ₁	8.4+1.5/-0	8.4+1.5/-0	8.4+1.5/-0	12.4+2.0/-0
A	178.0±0.10	250.0±1.0	330.0±1.0	178.0±0.10
N	60.5±1.0	100.0±1.0	100±1.0	60.5±1.0

9-1. CARDBOARD TAPE DIMENSIONS



9-2. EMBOSSED TAPE DIMENSIONS



Size	0402	0603		0805		1206			1210	
Chip Thickness	0.50±0.05	0.80±0.07	0.80±0.15/-0.10	0.80±0.10	1.25±0.10 1.25±0.20	0.80±0.10	0.95±0.10 1.25±0.10	1.60±0.20 1.60 ^{+0.30/-0.10}	0.95±0.10 1.25±0.10 1.60±0.20 2.00±0.20	2.50±0.30
A ₀	0.62±0.05	1.00±0.05/-0.10	1.02±0.05/-0.10	1.50±0.10	<1.65	2.00±0.10	<2.00	<2.00	<3.05	<3.10
B ₀	1.12±0.05	1.80±0.10	1.80±0.10	2.30±0.10	<2.40	3.50±0.10	<3.60	<3.70	<3.80	<4.00
T	0.60±0.05	0.95±0.05	0.97±0.05	0.95±0.05	0.23±0.05	0.95±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.23±0.05
K ₀	-	-	-	-	<2.50	-	<2.50	<2.50	<2.50	<3.50
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P ₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP ₀	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20
P ₁	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
P ₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D ₀	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05	1.50±0.10/-0.10	1.55±0.05	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10
D ₁	-	-	-	-	1.00±0.10	-	1.00±0.10	1.00±0.10	1.00±0.10	1.00±0.10
E	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05

Size	1808		1812		1825		2220		2225	
Chip Thickness	1.25±0.10 1.60±0.20	2.00±0.20	1.25±0.10 1.60±0.20 2.00±0.20	2.50±0.30	1.60±0.20 2.00±0.20	2.50±0.30	1.40±0.15 1.60±0.20 2.00±0.20	2.50±0.30	2.00±0.20	2.50±0.30
A ₀	<2.50	<2.50	<3.90	<3.90	<6.80	<6.80	<5.80	<5.80	<6.80	<6.80
B ₀	<5.30	<5.30	<5.30	<5.30	<5.30	<5.30	<6.50	<6.50	<6.50	<6.50
T	0.25±0.05	0.25±0.05	0.25±0.05	0.25±0.05	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10
K ₀	<2.50	<2.50	<2.50	<3.00	<2.50	<3.10	<2.50	<3.10	<2.50	<3.10
W	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20
P ₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP ₀	40.0±0.20	40.0±0.20	40.0±0.20	40.0±0.20	40.0±0.20	40.0±0.20	40.0±0.20	40.0±0.20	40.0±0.20	40.0±0.20
P ₁	4.00±0.10	4.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P ₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D ₀	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10	1.50±0.10/-0.10
D ₁	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10
E	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05

10.APPLICATION NOTES

STORAGE

To prevent the damage of solderability of terminations, the following storage conditions are recommended:

Indoors under 5 ~ 40°C and 20% ~ 70% RH.

No harmful gases containing sulfuric acid, ammonia, hydrogen sulfide or chlorine.

Packaging should not be opened until the capacitors are required for use. If opened, the pack should be re-sealed as soon as is practicable. Taped product should be stored out of direct sunlight, which might promote deterioration in tape or adhesion performance. The capacitors should be used within 6 months and checked the solderability before use.

HANDLING

Chip capacitors are dense, hard, brittle, and abrasive materials. They are liable to suffer mechanical damage, in the form of cracks or chips. Chip Capacitors should be handled with care to avoid contamination or damage. To use vacuum or plastic tweezers to pick up or plastic tweezers is recommended for manual placement. Tape and reeled packages are suitable for automatic pick and placement machine.

PREHEAT

In order to minimize the risk of thermal shock during soldering, a carefully controlled preheat is required. The rate of preheat should not exceed 4°C per second and the final preheat temperature should be within 100°C of the soldering temperature for small chips such as 0402, 0603, 0805 and 1206, within 50°C of the soldering temperature for bigger chips such as 1210, 1808, 1812, 1825, 2220 and 2225, etc.

SOLDERING

Use mildly activated rosin RA and RMA fluxes do not use activated flux. The amount of solder in each solder joint should be controlled to prevent the damage of chip capacitors caused by the stress between solder, chips, and substrate.

Hand soldering with temperature-controlled iron not exceeding 30 watts and diameter of tip less than 1.2 mm is recommended, tip of iron should not contact the ceramic body directly, and the temperature of iron should be set to not more than 260°C.

For bigger chips such as 1210, 1808, 1812, 2220 and 2225, etc. wave soldering and hand soldering are not recommended.

Refer IPC/JEDEC J-STD-020D Method recommended soldering profiles :

Reflow not sooner than 15 minutes and not longer than 4 hrs after removal from the temperature/humidity chamber, subject the sample to 3 cycle of the appropriate reflow conditions as defined as below Table description.


Profile Feature	Pb-Free Assembly
Preheat/Soak	
Temperature Min.(T _{min})	150°C
Temperature Max.(T _{max})	200°C
Time(t _s) from (T _{min} to T _{max})	60 to 120 seconds
Ramp-up rate(T _L to T _p)	3°C/second max.
Liquidous temperature(T _L)	217°C
Time(t _L) maintained above T _L	60 to 150 seconds
Peak package body temperature(T _p)	For user T _p must not exceed the Classification temp 260°C For suppliers T _p must equal or exceed the Classification temp 260°C
Time(T _p)* within 5°C of the specified classification temperature(T _c)	30* second
Ramp-down rate (T _p to T _L)	6°C/second max.
Time 25°C to peak temperature 260°C	8 minutes max.

Lead-free : Soldering temperature = 235 to 260°C, depending on product.

Maximum temperature = Minimum temperature (235°C)+ ΔT + Tolerance for oven process and measurement(5 ~ 7°C)

Time at peak temperature = 10sec, Dwell above 217°C = 90sec, Ramping rate = 3°C/sec(heating) and 6°C/sec(heating).

Classification Reflow Profiles



Chip Size	ΔT
0402, 0603, 0805, 1206	100 °C
1210, 1808, 1812, 2211, 2220, 2225	50 °C

Soldering	Solder Temp. (T_c)	Soldering Time (t_p)
Reflow	235 – 260 °C	< 15 sec.
Wave	230 – 260 °C	< 5 sec.

Note : For example , T_c is 260°C and time t_p is 15sec.

for user : The peak temperature must not exceed 260°C . The time above 255°C must not exceed 15 seconds.

COOLING

After soldering, cool the chips and the substrate gradually to room temperature. Natural cooling in air is recommended to minimize stress in the solder joint. A cooling rate not exceeding 4°C per second should be used when forced cooling is necessary.

CLEANING

All flux residues must be removed by using suitable electronic-grade vapor-cleaning solvents to eliminate contamination that could cause electrolytic surface corrosion. Good results can be obtained by using ultrasonic cleaning of the solvent. The choice of the proper system is depends upon many factors such as component mix, flux, and solder paste and assembly method. The ability of the cleaning system to remove flux residues and contamination from under the chips is very important.

11.REFERENCE TABLE

<u>FM</u>	<u>31</u>	<u>X</u>	<u>104</u>	<u>K</u>	<u>251</u>	<u>E</u>	<u>E</u>	<u>G</u>
PDC Family	Size	Dielectric	Capacitance	Tolerance	Rated voltage	Packaging	Thickness	Control Code
Table1.	Table2	Table3	Table4	Table5	Table6	Table7	Table8	Table9

Table 1 PDC family			
Code	Description	Code	Description
FM	100V ≤ Rated Voltage ≤ 630V series		

Table 2 EIA size			
General Purpose			
Code	Description	Code	Description
15	0402(1005)	43	1812 (4532)
18	0603 (1608)	46	1825 (4563)
21	0805 (2012)	52	2211 (5728)
31	1206 (3216)	55	2220 (5750)
32	1210 (3225)	56	2225 (5763)
42	1808 (4520)		

Table 3 Dielectric Material Characteristics			
Code	Description	Code	Description
N	C0G(NPO)	X	X7R
B	X5R	F	Y5V

Table 4 Capacitance Rule Code					
Two significant digits followed by no. of zeros. And R is in place of decimal point.					
Code	Description	Code	Description	Code	Description
R47	0.47pF	100	100=10x10 ⁰ =10pF	104	104=10x10 ⁴ =100nF
0R5	0.5pF	102	102=10x10 ² =1000pF	106	106=10x10 ⁶ =10μF

Table 5 Tolerance							
Code	Description	Code	Description	Code	Description	Code	Description
A	±0.05 pF	F	±1 %	J	±5 %	N	-5% ~ +10%
B	±0.10 pF	G	±2 %	K	±10 %	P	±0.02 pF
C	±0.25 pF	H	±3 %	L	0% ~ +10%	Q	±0.03 pF
D	±0.50 pF	I	-10% ~ 0%	M	±20 %	Z	-20% ~ 80%

Table 6 Rated voltage

General Purpose							
Code	Description	Code	Description	Code	Description	Code	Description
6R3	6.3VDC	101	100VDC	631	630VDC	302	3000VDC
100	10VDC	201	200VDC	102	1000VDC	402	4000VDC
160	16VDC	251	250VDC	152	1500VDC	502	5000VDC
250	25VDC	401	400VDC	202	2000VDC	602	6000VDC
500	50VDC	501	500VDC	252	2500VDC		

Table 7 Packaging Type

Code	Description	Code	Description
B	Bulk	T	Tray package
E	Tape and 7" Reel, Embossed Tape	P	Tape and 7" Reel, Paper Tape
K	Tape and 10" Reel, Embossed Tape	D	Tape and 10" Reel, Paper Tape
L	Tape and 13" Reel, Embossed Tape	G	Tape and 13" Reel, Paper Tape

Table 8 Thickness Description

Code	Description	Code	Description	Code	Description
A	0.60 ± 0.10 mm	I	1.25 ± 0.20 mm	Q	0.50 + 0.02/-0.05 mm
B	0.8 + 0.15/-0.10 mm	J	1.15 ± 0.15 mm	R	3.10 ± 0.30 mm
C	1.25 ± 0.10 mm	K	0.50 ± 0.20 mm	S	0.80 ± 0.07 mm
D	1.40 ± 0.15 mm	L	0.30 ± 0.03 mm	T	0.85 ± 0.10 mm
E	1.60 ± 0.20 mm	M	0.95 ± 0.10 mm	U	0.50 ± 0.10 mm
F	2.00 ± 0.20 mm	N	0.50 ± 0.05 mm	V	0.20 ± 0.02 mm
G	2.50 ± 0.30 mm	O	3.50 ± 0.20 mm	X	0.80 ± 0.10 mm
H	2.80 ± 0.30 mm	P	1.60 +0.3/-0.10 mm	Z	0.25 ± 0.03 mm

Table 9 Special Control Code

Code	Description	Code	Description
G	RoHS Compliant		